



**Fraunhofer**

**TESTED<sup>®</sup>  
DEVICE**

PPS  
King GMP  
**Report No. PF 2305-1421**

DUPLICATE

Statement of  
Qualification

Single product  
Particle Emission

Customer

Pfennig Reinigungstechnik GmbH  
Heubachstrasse 1  
87471 Durach  
Germany

Component tested

Category:

Materials

Subcategory:

Consumables

Product name:

King GMP  
(manufacturing date: 11/28/2022; color: white; material: 100 % poly-  
ester; article number: 3500051; charge number: V2022/11; pre-treatment:  
washed)

Random sampling of particle emissions (airborne)

Standards/Guidelines:

ISO 14644-1, -14; VDI 2083 Part 9.2, Part 9.1 (without 24-hour running-in period)  
The norms stated generally refer to the version valid at the time of the tests.

Test devices:

Optical particle counter:  
LasAir II 110 with measuring ranges  $\geq 0.1\text{ }\mu\text{m}$ ,  $\geq 0.2\text{ }\mu\text{m}$ ,  $\geq 0.3\text{ }\mu\text{m}$ ,  $\geq 0.5\text{ }\mu\text{m}$ ,

Test environment parameters:

- Cleanroom Air Cleanliness Class (according to ISO 14644-1):..... ISO 1
- Airflow velocity:.....0.45 m/s
- Airflow pattern:..... vertical laminar flow
- Temperature: .....22 °C  $\pm$  0.5 °C
- Relative humidity: ..... 45 %  $\pm$  5 %

Test procedure parameters:

Test bench according to ISO 9073-10:

- Sample clamping position:..... flat
- Length between clamping points: ..... 230 mm
- Motion cycle:
  - Linear compression s:..... 120 mm
  - Torsion: ..... 180 °
- Cycle time t: ..... 1 s
- Sampling chamber:.....none
- Duration of stress applied to test piece: ..... 100 min
- Distance between particle counting probe and test piece:..... 130 mm

Test result / Classification

When operated in a dry state using the given test parameters, the mop King GMP is suitable for use in cleanrooms up to the following Air Cleanliness Class according to ISO 14644-1:

| Test parameter(s)                                                    | Air Cleanlines Class |
|----------------------------------------------------------------------|----------------------|
| Linear compression = 120 mm<br>Torsion = 180 °<br>Cycle time t = 1 s | 6                    |
| Overall result                                                       |                      |

This corresponds with ISO-ACP<sub>c</sub> Class 6 according to VDI 2083 Part 9.2.

Please note: Transport damages, incorrect installation, aging behavior etc. can influence the test result.

The measuring devices used for the qualification tests are calibrated at regular intervals; their results can be traced back to national and international standards. In cases where no national standards exist, the test procedure implemented complies with the technical regulations and norms applicable at the time of the test. The relevant documentation can be viewed on request at any time.

Detailed information and parameters of the test environment can be found in the Fraunhofer IPA test report.

Fraunhofer Institute for Manufacturing Engineering and Automation IPA

Department of Ultraclean Technology and Micromanufacturing

Nobelstrasse 12  
70569 Stuttgart  
Germany

PF 1807-1056

Report No. first document

Stuttgart, August 31, 2018

Place, date of first document issued

PF 2305-1421

Report No. current document

Stuttgart, November 16; 2023

Place, current date

on behalf of

Dr.-Ing. Frank Bürger, Project Manager Fraunhofer IPA